

PRODUCT AH-4075PMA/XYL

1. GENERAL DESCRIPTION

- A variety of two-component Polyurethane Coating can be as a hardener

2. FEATURES

- Weather resistance
- Flexibility

3. APPLICATIONS

- Automobile repair, Heavy duty protective coating
- Wood, Metal
- Plastic, Synthetic leather
- Adhesives, Film coating

4. SPECIFICATIONS

Property	Unit	Value
Non Volatile Content	-	74.0 - 76.0
Viscosity (25 °C)	Gardner	E - H
NCO CONTENT	%	16.2 - 16.8
Free Monomer	%	0.5 Max

5. GUIDELINES for USE

- Be sure to read the MSDS, Technical data and Warnings before using please.
- Likely to result in injury due to solvent vapors compressed, please be careful.
- Has the possibility change the viscosity of the product when stored for a long time.

6. STORAGE GUIDE

- After use, the remaining sealed to prevent moisture from entering the indoor storage, please.

7. REFERENCES

- When used alone may be not cure.
- There is a possibility to be a compatibility problem when you use with another hardener.
- Mixed with the water-soluble resin used is the cause of the defects.

This document is prepared by SRC INTERNATIONAL authorized person. For more information please visit www.srcinterlog.com

ÇINARLI, 1563 Sk. No:2, İNCİ TOWER D:65; P:35170, Konak, İZMİR - TURKEY
Tel: +90 530 592 9719 info@srcinterlog.com

