

ALKYD FA60 W70 – Long Oil Alkyd Resin

DESCRIPTION

ALKYD FA60 W70 is a Soybean Fatty Acid Based glossy air-drying Long Oil Alkyd Resin.

PRINCIPLE PROPERTIES

- ✓ Very good brushability
- Very high outdoor color durability and gloss retention
- ✓ Very good yellowing resistance
- ✓ Good through drying and hardening

RECOMENDED APPLICATIONS

✓ Air drying all interior and exterior architectural finishes, primers and undercoats

SOLUBILITY

Solvent Type	Solubility	
Toluene	+	
Xylene	+	
White Spirit	+	
n-Buthanol	N 400	
Methy-Ethyl Ketones	+	
Glycol Ethers	+	

COMPATIBILITY

Resin Type	Compatibility
Rosin Esters	and a second sec
Amino Resins	161 N 1
Short Oil Alkyds	A Real Property in the
Medium Oil Alkyds	+
Long Oil Alkyds	+
Aliphatic Hardeners	+
Aromatic Hardeners	+
Cellulosic Resin	-
Phenoic Resin	-

TECHNICAL SPECIFICATIONS

Composition		
Oil type	Soybean Fatty Acid	
Oil Lenght, %	~60%	
Solvent	White Spirit	
PA Content %	%15	
Appearence	Clear	
OH%	1,4	
Test	Range	Method
Non Volatile, %	70±2 %	ISO 3251
Viscosity (25°C/%60) Pa.s	4,5 - 8	ISO 3219
Acid Value (mgKOH/g)	10 max	ISO 2114
Color (Gardner)	6 max	ISO 4630-2
Density (g/cm ³)	0.95±0,02	ISO 2811-1

PACKAGING AND DELIVERY FORM

Resin is supplied in steel drum with net content of 190 Kg per drum. For the other package condition, please contact with us.

RECOMMENDED DRIER COMBINATIONS

Cobalt	<mark>0.0</mark> 4 - 0.06 %
Zr	0.05 - 0.07 %
Calcium	0.08 - 0.10 %

- As metals in relation to 100% resin

STORAGE AND SHELF LIFE

Store in at temperatures between 5-30 °C, wellsealed packaging, dry and well-ventilated storage, should be avoided from direct sunlight. Storage Shelf Life – 12 months from date of production.

MATERIAL SAFETY

Before handling the product , SDS should always be read and well understood. Safety prodecures should be followed.

This document is prepared by SRC INTERNATIONAL authorized person. For more information please visit www.srcinterlog.com

ÇINARLI, 1563 Sk. No:2, İNCİ TOWER D:65; P:35170, Konak, İZMİR - TURKEY Tel: +90 530 592 9719 info@srcinterlog.com