

ALKYD UR FA52 W60 – Urethane Alkyd Resin

DESCRIPTION

ALKYD UR FA52 W60 is Soybean Fatty Acid based on TDI modified Medium Oil Alkyd Resin.

PRINCIPLE PROPERTIES

- ✓ Very good brushability and sprayability
- ✓ Excellent drying and hardness
- ✓ Good color and gloss retention
- ✓ Good water resistance

RECOMENDED APPLICATIONS

- ✓ Special yacht and parquet varnishes
- ✓ Air drying wood applications
- ✓ Marine paints and industrial applications

SOLUBILITY

Solvent Type	Solubility
Toluene	+
Xylene	+
White Spirit	+
n-Butanol	-
Methy-Ethyl Ketones	+
Glycol Ethers	+

COMPATIBILITY

Resin Type	Compatibility
Rosin Esters	-
Amino Resins	-
Short Oil Alkyds	-
Medium Oil Alkyds	+
Long Oil Alkyds	+
Aliphatic Hardeners	+
Aromatic Hardeners	+
Cellulosic Resin	-
Phenolic Resin	-

TECHNICAL SPECIFICATIONS

Composition		
Oil type	Soybean Oil Fatty Acid	
Oil Length, %	~52%	
Solvent	White Spirit	
PA Content %	21%	
Appearance	Clear	
Test	Range	Method
Non Volatile, %	60±2 %	ISO 3251
Viscosity (25°C) Pa.s	4 - 10	ISO 3219
Acid Value (mgKOH/g)	5 max	ISO 2114
Color (Gardner)	7 max	ISO 4630-2
Density (g/cm ³)	0.95±0,02	ISO 2811-1

PACKAGING AND DELIVERY FORM

Resin is supplied in steel drum with net content of 190 Kg per drum. For the other package condition, please contact with us.

RECOMMENDED DRIER COMBINATIONS

Cobalt	0.04 - 0.06 %
Zr	0.05 - 0.07 %
Calcium	0.08 - 0.10 %

- As metals in relation to 100% resin

STORAGE AND SHELF LIFE

Store in at temperatures between 5-30 °C, well-sealed packaging, dry and well-ventilated storage, should be avoided from direct sunlight.

Storage Shelf Life – 12 months from date of production.

MATERIAL SAFETY

Before handling the product , SDS should always be read and well understood.

Safety prodecures should be followed.

This document is prepared by SRC INTERNATIONAL authorized person. For more information please visit www.srcinterlog.com