

PRODUCT AT-2150

1. GENERAL DESCRIPTION

- A variety of two-component Polyurethane Coating can be as a hardener

2. FEATURES

- Fast dry
- Hardness
- Compatibility with polyol

3. APPLICATIONS

- Wood
- Polyurethane varnish
- Stamping hoil
- Synthetic leather

4. SPECIFICATIONS OF RESIN

Property	Unit	Value
Non Volatile Content	-	49.0 - 51.0
Viscosity (25°C)	Gardner	T - V
	cps	600 - 1,000
NCO CONTENT	%	7.8 - 8.2
Free Monomer	%	1.0 Max

5. USE OF RESIN

- Be sure to read the MSDS, Technical data and Warnings before using please.
- Likely to result in injury due to solvent vapors compressed, please be careful.
- Has the possibility change the viscosity of the product when stored for a long time.

6. STORAGE AND REMAINING GUIDE & SAFETY

- After use, the remaining sealed to prevent moisture from entering the indoor storage, please.

7. REFERENCES

- When used alone may be not cure.
- There is a possibility to be a compatibility problem when you use with another hardener.
- Mixed with the water-soluble resin used is the cause of the defects.

This document is prepared by SRC INTERNATIONAL authorized person. For more information please visit www.srcinterlog.com

**ÇINARLI, 1563 Sk. No:2, İNCİ TOWER D:65; P:35170, Konak, İZMİR - TURKEY
Tel: +90 530 592 9719 info@srcinterlog.com**